

Pegasus® Granular

0-0-62

	6	• , •
Chemical	്റന	nosition
Chernea		posición

Component	Symbol	Typical	Guarantee
Potassium Oxide Equivalent	K ₂ O	62.5 %	62% Minimum
Potassium Chloride	KCI	98.9 %	
Sodium Chloride	NaCl	1.0 %	
Chloride	Cl-	47.6 %	
Moisture	H ₂ O	0.05 %	

Particle Size Distribution Cumulative %

Tyler Mesh	US Mesh	Opening (mm)	Typical Range	Typical
4	4	4.75	0 - 2	0.6
5	5	4.00	3 - 15	8
6	6	3.35	20 - 50	34
7	7	2.80	50 - 75	65
8	8	2.36	75 - 95	89
9	10	2.00	93 - 100	98
10	12	1.70	97 - 100	99

Physical Properties	
Parameter	Typical
Bulk Density (Loose)	
- lb/ft ³	65
- kg/m³	1041
Angle of Repose	36 Degrees

Sizing Characteristics	
Parameter	Typical
Size Guide Number (SGN)	305
Uniformity Index (UI)	54

Please refer to the Safety Data Sheet (SDS #: MOS100052) for additional information (www.mosaicco.com)

The information contained in this data sheet is a representation of the average properties of product analyses as tested on composite samples and typical analyses should not be considered a guaranteed specification. Individual shipment and grab sample analyses may fall outside of the above typical values Additional handling, transportation, or improper/extended storage may affect product analyses. Mosaic disclaims any responsibility or liability for any loss or damage that may occur from any reliance on, or other use of, the above information with respect to the product.